

Product Manual(TDS)

Urethane acrylate BW L426A

Product introduction

BW L426A is a polyurethane acrylate with high hardness, fast curing speed, good toughness and excellent tensile strength. Widely used in light curing 3D printing, UV nail polish, UV ink, providing good printing accuracy, toughness, tensile strength.

Product characteristics

Functional	2	Hardness	-
Active Ingredient (%)	100%	Proportion (25°C)	1.23
Appearance (25°C)	Transparent clear liquid	Shrinkage(%)	-
Viscosity (cps at 60°C)	400-1000	Refractive Index(n_d at 25°C)	1.53
Color (APHA)	≤ 60	Elongation At Break (%)	-
Acid Value (mg KOH/g)	≤ 1	Tensile Strength (MPa)	-

- High print accuracy;
- High hardness;
- Fast curing speed;
- Good tensile strength

Applications

- It is used in UV 3D printing, UV nail polish and UV ink.

Packaging

- In 20 kg plastic drums
- In 200 kg metal drums

Storage

- Store in a properly sealed container, away from sunlight and heat;
- At normal room temperature storage conditions, the product storage stability of at least 6 months;
- Low temperature or long-term storage, this product may form a false plastic layer;
- This rheological change can be restored by stirring or slight heating (Max temperature 45°C);

It is especially suggested that the above data and suggestions are based on experimental data, but due to the uselessness of users, we can not provide any guarantee for the integrity and accuracy of the information.

We recommend that customers choose our products and adopt them. Determine their applicability before making our recommendations.

