

# **Product Manual(TDS)**

## **Urethane acrylate BW L435**

#### **Product introduction**

**BW L435** is a two-functional aliphatic polyurethane acrylate; with fast curing speed, good toughness and excellent abrasion resistance, etc., especially suitable for UV nail polish glue, light-curing 3D printing, plastic paints, resilient parquet flooring paint and other fields, providing excellent impact resistance and flexibility.

### **Product characteristics**

| Functional              | 2                        | Hardness                     | -    |
|-------------------------|--------------------------|------------------------------|------|
| Active Ingredient (%)   | 100%                     | Proportion (25°C)            | 1.07 |
| Appearance (25°C)       | Transparent clear liquid | Shrinkage(%)                 | -    |
| Viscosity (cps at 60°C) | 7000-15000               | Refractive Index(nd at 25°C) | 1.49 |
| Color (APHA)            | $\leq 60$                | Elongation At Break (%)      | -    |
| Acid Value (mg KOH/g    | $(g) \leq 1$             | Tensile Strength (MPa)       | -    |
|                         |                          |                              |      |

- High flexibility;
- Fast curing speed;
- Resistant to reverse shock

### Applications

• It is used in UV 3D printing, UV nail polish and UV coating.

### Packaging

- In 20 kg plastic drums
- In 200 kg metal drums

#### **Storage**

- Store in a properly sealed container, away from sunlight and heat;
- At normal room temperature storage conditions, the product storage stability of at least 6 months;
- Low temperature or long-term storage, this product may form a false plastic layer;
- This rheological change can be restored by stirring or slight heating (Maximum temperature 45°C);

It is especially suggested that the above data and suggestions are based on experimental data, but due to the

uselessness of users, we can not provide any guarantee for the integrity and accuracy of the information.

We recommend that customers choose our products and adopt them. Determine their applicability before

#### making our recommendations.

A 广州市番禺区番禺大道北555号天安节能科技园产业大厦1座904

904. NO. 1 Building, Tianan Hi- tech Ecological Park.No.555 panyu road North, Panyu,Guangzhou T 020- 3107 4363 F 020- 3107 4309 E contact@bawo-chem.com W www.bawo-chem.com Factory : Guangdong · Yingde 无锡公司&研发中心: 江苏无锡市锡山开发区科技创业园 制造基地地址: 广东英德市东华镇高新技术产业园

