

# **Product Manual(TDS)**

# **Urethane acrylate BW L8450**

#### **Product introduction**

**BW L8450** is an aliphatic polyurethane acrylate. It has the characteristics of low heat release, good toughness and high permeability. Mainly used in nail polish extension layer, and has good interlayer adhesion, toughness. Its colloid has excellent appearance characteristics such as strong transmission and no yellow phase.

#### **Product characteristics**

Functional	2	Hardness	82D
Active Ingredient (%)	100%	Proportion (25°C)	1.17
Appearance (25°C) Tran	sparent clear liquid	Shrinkage(%)	-
Viscosity (cps at 60°C)	5000-10000	Refractive Index(nd at 25°C)	1.49
Color (APHA)	≤60	Elongation At Break (%)	-
Acid Value (mg KOH/g)	≤1	Tensile Strength (MPa)	-

- Low heat release;
- High transmittance;
- Good toughness;

#### **Applications**

• It is used in LED UV nail polish extension layer, 3D printing, UV adhesive.

### **Packaging**

- In 20 kg plastic drums
- In 200 kg metal drums

## **Storage**

- Store in a properly sealed container, away from sunlight and heat;
- At normal room temperature storage conditions, the product storage stability of at least 6 months;
- Low temperature or long-term storage, this product may form a false plastic layer;
- This rheological change can be restored by stirring or slight heating (Maximum temperature 45°C);

It is especially suggested that the above data and suggestions are based on experimental data, but due to the uselessness of users, we can not provide any guarantee for the integrity and accuracy of the information.

We recommend that customers choose our products and adopt them. Determine their applicability before

A 广州市番禺区番禺大道北555号天安节能科技园产业大厦1座904

904. NO. 1 Building, Tianan Hi- tech Ecological Park.No.555 panyu road North, Panyu,Guangzhou

T 020- 3107 4363 F 020- 3107 4309 E contact@bawo-chem.com W www.bawo-chem.com Factory: Guangdong · Yingde



making our recommendations.



