



Product Manual(TDS)

Urethane acrylate BW 8298

Product introduction

BW 8298 is a high tenacity, weathering resistant aliphatic six-functional polyurethane acrylate. It is particularly suitable for vacuum plating, plastic, furniture and parquet paints and inks, providing good weathering resistance, excellent toughness and heat resistance and good chemical resistance.

Product characteristics

Functional	6	Hardness	-
Active Ingredient (%)	100%	Proportion (25°C)	1.17
Appearance (25°C)	Clear transparent liquid	Shrinkage(%)	-
Viscosity (cps at 25°C)	6000-15000	Refractive Index(n_d at 25°C)	1.49
Color (APHA)	≤ 60	Elongation At Break (%)	-
Acid Value (mg KOH/g)	≤ 1	Tensile Strength (MPa)	-

- Good weathering resistance;
- Good heat resistance;
- Good toughness;
- Excellent chemical resistance;

Applications

- It is used in vacuum plating, UV plastics spraying, UV lacquers for furniture and parquet, etc.

Packaging

- In 20 kg plastic drums
- In 200 kg metal drums

Storage

- Store in a properly sealed container, away from sunlight and heat;
- At normal room temperature storage conditions, the product storage stability of at least 6 months;
- Low temperature or long-term storage, this product may form a false plastic layer;
- This rheological change can be restored by stirring or slight heating (up to 45°C);

It is especially suggested that the above data and suggestions are based on experimental data, but due to the uselessness of users, we can not provide any guarantee for the integrity and accuracy of the information.

We recommend that customers choose our products and adopt them. Determine their applicability before making our recommendations.

